CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	CP-2020-05-26-90 Date: 21/02/2020
Customer	:	Assistant Executive Engineer,T Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC drain and road kempegowda Nagara 6th A cross and 6th B cross roads in Dasarahalli ward no15
Agency	:	Hanumantharaju.B.T 1334 Anjanadri,7th Main 11th Cross OC Road 2nd Stage,Mahalakshmipuram Bangalore-86
Customer's Reference	:	EE/DD/W.O/467/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	15-02-20
Customer ID	:	M20 Bottom Slab
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	21/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Bottom Slab	M20	14/02/2020	21/02/2020	150.14 X 150.06 X 149.33	22530	8.089	414.9	18.4	18.6
2	M20 Bottom Slab	M20	14/02/2020	21/02/2020	150.68 X 150.67 X 151.68	22703	8.582	430.4	19.0	
3	M20 Bottom Slab	M20	14/02/2020	21/02/2020	150.96 X 150.86 X 149.41	22774	8.408	418.3	18.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಟಿ. ದಾಸರಹಳ್ಳಿ ಉಪ ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಜಿ.ಜಿ.ಎಂ.ಪಿ.
ಬೆಂಗಳೂರು-560073.

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 13/03/2020

Lab ID	:	CP-2020-05-26-90
Customer	:	Assistant Executive Engineer,T Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC drain and road kempegowda Nagara 6th A cross and 6th B cross roads in Dasarahalli ward no15
Agency	:	Hanumantharaju.B.T 1334 Anjanadri,7th Main 11th Cross OC Road 2nd Stage,Mahalakshmipuram Bangalore-86
Customer's Reference	:	EE/DD/W.O/467/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	15-02-20
Customer ID	:	M20 Bottom Slab
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	13/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Bottom Slab	M20	14/02/2020	13/03/2020	150.22 X 150.54 X 150.55	22535	8	536	24	23.2
2	M20 Bottom Slab	M20	14/02/2020	13/03/2020	150.22 X 150.54 X 150.55	22788	8	502	22	
3	M20 Bottom Slab	M20	14/02/2020	13/03/2020	150.22 X 150.54 X 150.55	22443	8	537	24	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತ
ಟಿ. ದಾಸರಹಳ್ಳಿ ಉಪ ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿ.ಬಿ.ಎಂ.ಪಿ.
ಬೆಂಗಳೂರು-560073.

CIVIL Pro BANGALORE Sig Date

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5542

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 21/02/2020

Lab ID	:	CP-2020-05-26-90
Customer	:	Assistant Executive Engineer,T Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC drain and road kempegowda Nagara 6th A cross and 6th B cross roads in Dasarahalli ward no15
Agency	:	Hanumantharaju.B.T 1334 Anjanadri,7th Main 11th Cross OC Road 2nd Stage,Mahalakshmipuram Bangalore-86
Customer's Reference	:	EE/DD/W.O/467/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	15-02-20
Customer ID	:	M20 Bottom Slab
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	21/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Bottom Slab	M20	14/02/2020	21/02/2020	150.59 X 149.98 X 149.63	22585	8.089	410.1	18.2	18.4
2	M20 Bottom Slab	M20	14/02/2020	21/02/2020	150.13 X 151.55 X 149.55	22751	8.582	415.9	18.3	
3	M20 Bottom Slab	M20	14/02/2020	21/02/2020	149.97 X 151.76 X 149.92	22759	8.408	424.4	18.6	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಾಮಗ್ರಿ ಪರೀಕ್ಷಕ ಅಭಿಯಂತರರು
ಟಿ. ದಾಸರಹಳ್ಳಿ ಉಪ ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ. ಜಿ.ಜಿ.ಎಂ.ಪಿ.
ಬೆಂಗಳೂರು-560073.

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 13/03/2020

Lab ID	:	CP-2020-05-26-90
Customer	:	Assistant Executive Engineer,T Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC drain and road kempegowda Nagara 6th A cross and 6th B cross roads in Dasarahalli ward no15
Agency	:	Hanumantharaju.B.T 1334 Anjanadri,7th Main 11th Cross OC Road 2nd Stage,Mahalakshmipuram Bangalore-86
Customer's Reference	:	EE/DD/W.O/467/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	15-02-20
Customer ID	:	M20 Bottom Slab
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	13/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Bottom Slab	M20	14/02/2020	13/03/2020	150.22 X 150.54 X 150.55	22694	8	525	23	22.8
2	M20 Bottom Slab	M20	14/02/2020	13/03/2020	150.22 X 150.54 X 150.55	22569	8	499	22	
3	M20 Bottom Slab	M20	14/02/2020	13/03/2020	150.22 X 150.54 X 150.55	22595	8	521	23	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರ
ಟಿ. ದಾಸರಹಳ್ಳಿ ಉಪ ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿ.ಬಿ.ಎಂ.ಪಿ
ಬೆಂಗಳೂರು 560073.

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 23/02/2020

Lab ID	:	CP-2020-05-26-90
Customer	:	Assistant Executive Engineer,T Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC drain and road kempegowda Nagara 6th A cross and 6th B cross roads in Dasarahalli ward no15
Agency	:	Hanumantharaju.B.T 1334 Anjanadri,7th Main 11th Cross OC Road 2nd Stage,Mahalakshmipuram Bangalore-86
Customer's Reference	:	EE/DD/W.O/467/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-02-20
Customer ID	:	M20 Side Wall
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	23/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm²)	Average Compressive Strength (N/mm²)
1	M20 Side Wall	M20	16/02/2020	23/02/2020	150.63 X 151.00 X 150.20	22745	8.089	425.4	18.7	18.8
2	M20 Side Wall	M20	16/02/2020	23/02/2020	149.27 X 151.41 X 149.88	22601	8.582	422.6	18.7	
3	M20 Side Wall	M20	16/02/2020	23/02/2020	149.18 X 151.15 X 149.78	22549	8.408	428.1	19.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಟಿ. ದಾಸರಹಳ್ಳಿ ಉಪ ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ. ಜಿ.ಜಿ.ಎಂ.ಪಿ.
ಬೆಂಗಳೂರು-560073.

CIVIL PRO BANGALORE Sig. Date

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 15/03/2020

Lab ID	:	CP-2020-05-26-90
Customer	:	Assistant Executive Engineer,T Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC drain and road kempegowda Nagara 6th A cross and 6th B cross roads in Dasarahalli ward no15
Agency	:	Hanumantharaju.B.T 1334 Anjanadri,7th Main 11th Cross OC Road 2nd Stage,Mahalakshmipuram Bangalore-86
Customer's Reference	:	EE/DD/W.O/467/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-02-20
Customer ID	:	M20 Side Wall
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	15/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Side Wall	M20	16/02/2020	15/03/2020	150.22 X 150.54 X 150.55	23013	8	539	23	23.3
2	M20 Side Wall	M20	16/02/2020	15/03/2020	150.22 X 150.54 X 150.55	22657	8	515	23	
3	M20 Side Wall	M20	16/02/2020	15/03/2020	150.22 X 150.54 X 150.55	22697	8	540	24	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಟಿ. ದಾಸರಹಳ್ಳಿ ಉಪ ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಜಿ.ಪಿ.ಎಂ ಟಿ
ಬೆಂಗಳೂರು-560073.

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2020-05-26-90 **Date: 18/03/2020**

Customer : Assistant Executive Engineer,T Dasarahalli Sub Division, BBMP, Bangalore.

Address : T Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Improvements of CC drain and road kempegowda Nagara 6th A cross and 6th B cross roads in Dasarahalli ward no15

Agency : Hanumantharaju.B.T 1334 Anjanadri,7th Main 11th Cross OC Road 2nd Stage,Mahalakshmipuram Bangalore-86

Customer's Reference : EE/DD/W.O/467/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-02-20

Customer ID : Precast Slab 100mm

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Precast Slab 100mm	M30	19/02/2020	18/03/2020	150.22 X 150.54 X 150.55	22955.56	8.08	777.08	33.85	33.56
2	Precast Slab 100mm	M30	19/02/2020	18/03/2020	150.22 X 150.54 X 150.55	22727.22	8.31	747.49	32.89	
3	Precast Slab 100mm	M30	19/02/2020	18/03/2020	150.22 X 150.54 X 150.55	22830.15	8.03	774.52	33.93	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರ
ಟಿ. ದಾಸರಹಳ್ಳಿ ಉಪ ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ. ಜಿ.ಜಿ.ಎಂ.ಪಿ
ಬೆಂಗಳೂರು-560073

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 26/02/2020

Lab ID	:	CP-2020-05-26-90
Customer	:	Assistant Executive Engineer,T Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC drain and road kempegowda Nagara 6th A cross and 6th B cross roads in Dasarahalli ward no15
Agency	:	Hanumantharaju.B.T 1334 Anjanadri,7th Main 11th Cross OC Road 2nd Stage,Mahalakshmipuram Bangalore-86
Customer's Reference	:	EE/DD/W.O/467/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-02-20
Customer ID	:	Precast Slab 100mm
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	26/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Precast Slab 100mm	M30	19/02/2020	26/02/2020	150.22 X 150.54 X 150.55	22934.9	8.2	579.7	25.3	25.4
2	Precast Slab 100mm	M30	19/02/2020	26/02/2020	150.22 X 150.54 X 150.55	22700.7	8.5	597.1	26.3	
3	Precast Slab 100mm	M30	19/02/2020	26/02/2020	150.22 X 150.54 X 150.55	22929.2	8.1	561.9	24.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಎಂ.
ಟಿ. ದಾಸರಹಳ್ಳಿ ಉಪ ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಜಿ.ಜಿ.ಎಂ.ಪಿ.
ಬೆಂಗಳೂರು-560073.

CIVIL Pro BANGALORE Sig. Date.

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 18/03/2020

Lab ID	:	CP-2020-05-26-90
Customer	:	Assistant Executive Engineer,T Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC drain and road kempegowda Nagara 6th A cross and 6th B cross roads in Dasarahalli ward no15
Agency	:	Hanumantharaju.B.T 1334 Anjanadri,7th Main 11th Cross OC Road 2nd Stage,Mahalakshmipuram Bangalore-86
Customer's Reference	:	EE/DD/W.O/467/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-02-20
Customer ID	:	Precast Slab 100mm
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	18/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Precast Slab 100mm	M30	19/02/2020	18/03/2020	150.22 X 150.54 X 150.55	22674.22	8.29	755.24	33.31	32.87
2	Precast Slab 100mm	M30	19/02/2020	18/03/2020	150.22 X 150.54 X 150.55	22564.08	8.21	728.22	32.27	
3	Precast Slab 100mm	M30	19/02/2020	18/03/2020	150.22 X 150.54 X 150.55	22387.15	8.40	739.58	33.04	

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

ಸಾಮರ್ಥ್ಯಾಧಿಕಾರಿಯವರು
ಟಿ. ದಾಸರಹಳ್ಳಿ ಉಪ ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಜಿ.ಜಿ.ಎಂ.ಪಿ
ಬೆಂಗಳೂರು-560073.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1

****End of Report****

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 26/02/2020

Lab ID	:	CP-2020-05-26-90
Customer	:	Assistant Executive Engineer,T Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC drain and road kempegowda Nagara 6th A cross and 6th B cross roads in Dasarahalli ward no15
Agency	:	Hanumantharaju.B.T 1334 Anjanadri,7th Main 11th Cross OC Road 2nd Stage,Mahalakshmipuram Bangalore-86
Customer's Reference	:	EE/DD/W.O/467/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-02-20
Customer ID	:	Precast Slab 100mm
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	26/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Precast Slab 100mm	M30	19/02/2020	26/02/2020	150.22 X 150.54 X 150.55	23030.9	8.4	578.4	25.1	25.2
2	Precast Slab 100mm	M30	19/02/2020	26/02/2020	150.22 X 150.54 X 150.55	22813.4	8.1	601.3	26.4	
3	Precast Slab 100mm	M30	19/02/2020	26/02/2020	150.22 X 150.54 X 150.55	22603.4	8.1	547.8	24.2	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಮಾಂಪಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿ.
ಟಿ. ದಾಸರಹಳ್ಳಿ ಉಪ ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿ.ಬಿ.ಎಂ.ಪಿ.
ಬೆಂಗಳೂರು-560073.

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 18/03/2020

Lab ID	:	CP-2020-05-26-90
Customer	:	Assistant Executive Engineer,T Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC drain and road kempegowda Nagara 6th A cross and 6th B cross roads in Dasarahalli ward no15
Agency	:	Hanumantharaju.B.T 1334 Anjanadri,7th Main 11th Cross OC Road 2nd Stage,Mahalakshmipuram Bangalore-86
Customer's Reference	:	EE/DD/W.O/467/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-02-20
Customer ID	:	Precast Slab 100mm
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	18/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Precast Slab 100mm	M30	19/02/2020	18/03/2020	150.22 X 150.54 X ◊50.55	22719.19	8.29	765.17	33.68	33.33
2	Precast Slab 100mm	M30	19/02/2020	18/03/2020	150.22 X 150.54 X 150.55	22563.86	8.59	738.68	32.74	
3	Precast Slab 100mm	M30	19/02/2020	◊8/03/2020	150.22 X 150.54 X 150.55	22879.83	8.32	767.87	33.56	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ
ಇ. ದಾಸರಹಳ್ಳಿ ಉಪ ವಿಭಾಗ
ಹಾಗಲಗುಂಟೆ, ಜಿ.ಜಿ.ಎಂ.ಪಿ.
ಬೆಂಗಳೂರು-560073.

FOR CIVIL Pro.

CIVIL Pro BANGALORE Sig..... Date.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner